

ESSHETE 1250

TUBE AND PIPE, SEAMLESS

データシート

Esshete 1250 is a fully austenitic chromium-nickel steel with excellent high- temperature strength and good resistance to corrosion in boiler applications. The grade can be used at temperatures up to about 650°C (1200°F), it is easily fabricated and also characterized by:

- High strength in relation to other typical candidate austenitic alloys
- Very good resistance to steam and flue gas atmospheres
- Good structural stability at high temperatures
- Good weldability

STANDARDS

- : S21500
- : 1.4982
- : X10CrNiMoMnNbVB15-10-1

Product standards

- ASTM A213
- EN 10216-5

Approvals

- VdTÜV-Werkstoffblatt 520
- PED (Pressure Equipment Directive) 2014/68/EU

CHEMICAL COMPOSITION (NOMINAL)

Chemical composition (nominal) %

C	Si	Mn	P	S	Cr	Ni	Mo	V	Nb	B
0.1	0.5	6.3	≤0.035	≤0.015	15	9.5	1.0	0.3	1.0	0.005

APPLICATIONS

The high creep strength of Esshete 1250, combined with its good resistance to steam and flue gas atmospheres, makes it a very suitable material for use in coal-fired boilers. The grade was developed in the United Kingdom in the 1960's, and the bulk of the material has been used in the UK power industry in 500 and 660 MW boilers.

The main application has been superheaters and reheaters operating at 570°C (1058°F), steam pressure 170 bar (superheaters) and 40 bar (reheaters). Typical metal temperature 600–700°C (1112–1292°F), in flue gas temperature 900–1200°C (1652–2192°F). The corrosion environment on the fireside in the UK boilers was historically very aggressive as the British coal has, typically a high chlorine content of up to 0.6%, sulphur at 1–2% and a high ash content of 20%.

Esshete 1250 has also been used successfully in superheaters in biomass boilers, burning various biofuels and producing steam at 580–540°C (1076–1004°F) at 60–200 bars pressure.

Trademark information: Esshete 1250 is a trademark owned by Corus

CORROSION RESISTANCE

Air

Good resistance to scaling up to 800°C (1472°F).

Gaseous corrosion

Good resistance to steam and flue gas atmospheres. In service conditions typical of coal-fired boilers, the alloy has a very similar fireside corrosion to alloys of the ASTM 316H type. However, the much increased high-temperature strength gives significantly improved service performance. Fireside corrosion resistance in coal-fired, biomass-fired or coal/biomass co-fired boilers is similar to that of type ASTM 347H. Steam-side corrosion is similar to that of type ASTM 347H.

BENDING

Esshete 1250 can be cold bent to narrow bending radii. Heat treatment after cold bending is not normally necessary, but this must be decided after considering the degree of bending and the operating conditions.

If post bending heat treatment is carried out, it should be in the form of solution annealing.

Hot bending is carried out at 1100–850°C (1832–1652°F) and should be followed by solution annealing.

FORMS OF SUPPLY

Seamless tube and pipe in Esshete 1250 is supplied in dimensions up to 260 mm (10.24 in.) outside diameter, in the solution annealed and white-pickled condition or in the bright annealed condition.

HEAT TREATMENT

Tubes are delivered in the heat treated condition. If another heat treatment is needed after further processing the following is recommended:

Stress relieving

850–950°C (1560–1740°F), 10–15 minutes, cooling in air.

Solution annealing

1050–1150°C (1920–2100°F), 5–20 minutes, rapid cooling in air, gas or water.

MECHANICAL PROPERTIES

Metric units, at 20°C

Proof strength		Tensile strength	Elongation		Hardness
R _{p0.2} ^{a)}	R _{p1.0} ^{a)}	R _m	A ^{b)}	A ₂ ^{''}	HRB
MPa	MPa	MPa	%	%	
≥230	≥270	540–740	≥35	≥35	≤90

1 MPa = 1 N/mm²

Imperial units, at 68°F

Proof strength		Tensile strength	Elongation		Hardness
R _{p0.2} ^{a)}	R _{p1.0} ^{a)}	R _m	A ^{b)}	A ₂ ^{''}	HRB
ksi	ksi	ksi	%	%	

Imperial units

Temperature	Proof strength	
	R _{p.02}	R _{p1.0}
°F	ksi	ksi
	min.	min.
1200	18.7	23.9
1300	18.1	22.9

Creep strength

The creep rupture strength values correspond to values evaluated by Sterling tubes Ltd. The data from creep tests made by Sandvik correspond well to the given data.

Metric units

Temperature	Creep rupture strength, MPa		
	10 000 h	100 000 h	250 000h
°C			
600	241	199	177
610	231	185	158
620	221	167	134
630	210	147	109*
640	198	122	90*
650	184	100	78*
660	167	84	69*
670	147	74	52*
680	124	66	56*
690	102	59	51*
700	86	54	46*
710	75	49	42*
720	67	45	37*
730	61	40*	32*
740	55	36*	-
750	51	30*	-
760	46	-	-
770	42	-	-
780	38	-	-
790	34	-	-

* Values, which have involved extended stress/time extrapolation

Imperial units

Temperature	Creep rupture strength, ksi		
	10 000 h	100 000 h	250 000 h
°F			
1100	35.2	30.7	28.8
1125	33.9	27.2	23.3

Specific heat capacity¹⁾

Temperature, °C	J/kg °C	Temperature, °F	Btu/lb °F
20-800	575	68-1600	0.14
20-900	580	68-1800	0.14
20-1000	585	-	-

1) Mean values in temperature ranges

Thermal expansion¹⁾

Temperature, °C	Per °C	Temperature, °F	Per °F
20-100	15	68-200	8.5
20-200	16	68-400	9
20-300	17	68-600	9.5
20-400	18	68-800	10
20-500	18.5	68-1000	10.5
20-600	19	68-1200	10.5
20-700	19	68-1400	11
20-800	19.5	68-1600	11
20-900	20	68-1800	11
20-1000	20	-	-

1) Mean values in temperature ranges (x10⁻⁶)

Resistivity

Temperature, °C	μΩm	Temperature, °F	μΩin.
20	0.74	68	29.1
100	0.80	200	31.3
200	0.88	400	34.6
300	0.94	600	37.5
400	1.00	800	39.9
500	1.05	1000	41.8
600	1.09	1200	43.6
700	1.13	1400	45.1
800	1.16	1600	46.3
900	1.18	1800	47.2
1000	1.20	-	-

Modulus of elasticity¹⁾

Temperature, °C	MPa	Temperature, °F	ksi
20	192	68	27.8
100	184	200	26.6
200	176	400	25.5
300	168	600	24.2
400	160	800	22.9

