

EXERA® 5R10/2R25 MEDICAL WIRE WIRE

DATENBLATT

Exera® 5R10 and Exera® 2R25 are austenitic chromium-nickel stainless steels. Exera® 2R25 is a low carbon version of Exera® 5R10. The grades are characterized by:

- Good corrosion resistance
- Excellent toughness
- Good welding characteristics

STANDARDS

- : 304, 304L
- : S30400, S30403
- EN Number: 1.4301, 1.4306
- : X5CrNi18-10, X2CrNi19-11
- : 1.4301, 1.4306
- : X5 CrNi 18 10, X2 CrNi 19 11
- : 2332, 2352
- : Z6 CN 18 09, Z3 CN 18 10
- : 304S31

Product standards

- ASTM F899
- ISO 16061

APPLICATIONS

These grades are mainly used for surgical instruments and dental tools.

CHEMICAL COMPOSITION (NOMINAL) %

	C	Si	Mn	Cr	Ni
Exera® 5R10	≤0.07	≤0.75	≤2.0	18.5	9
Exera® 2R25	≤0.03	≤0.7	≤1.5	18.5	10

FORMS OF SUPPLY

Wire form

- In coils with weights up to 150 kg
- On various types of spool with wire weights up to 500 kg
- In straightened lengths up to 4 m

Surface finishes and size range

Surface finish	Size range, mm
Coated	0.20 - 8.00
Bright	0.11 - 0.80
Mechanically polished	0.40 - 6.00

MECHANICAL PROPERTIES

Typical mechanical properties for Exera® 5R10 and Exera® 2R25 at 20°C.

Grade	Tensile strength Rm	Proof strength Rp0.2	Elongation	Hardness	
	MPa	MPa	%	HRB	HB
Exera® 5R10	≥515	≥205	≥40	≤92	≤201
Exera® 2R25	≥485	≥170	≥40	≤92	≤201

PHYSICAL PROPERTIES

Typical physical properties for annealed Exera® 5R10 and Exera® 2R25 are given below :

Grade	Density	Elastic Modulus	Mean Coefficient of Thermal Expansion	Thermal Conductivity	Specific Heat	Resistivity
	g/cm ³	10 ³ MPa	mm/m/°C	W/m °C	J/kg °C	μΩm
			0-100 °C	at 100 °C	0-100 °C	20 °C
Exera® 5R10/2R25	8	193	17	16	500	0.72

CORROSION RESISTANCE

Excellent corrosion resistance in a wide range of atmospheric environments and various corrosive media.

Subject to pitting and crevice corrosion in warm chloride media and to stress corrosion cracking at temperatures above 60°C.

Considered resistant to potable water with up to approximately 200mg/l chlorides, at ambient temperatures, reducing to approximately 150 mg/l, at 60°C.

Haftungsausschluss: Sandvik bietet keine Produkte oder Dienstleistungen, die in irgendeiner Weise gedacht oder zu verstehen sind als Empfehlung oder anderweitige Beratung aus medizinischer/biologischer/sicherheitstechnischer Sicht in Bezug auf das Design, die Eignung, Angemessenheit oder Effektivität von medizinischen Werkstoffen, Instrumenten und/oder Medizingeräten.