

BOND XTC

WIRE INSULATIONS AND COATINGS

DATASHEET

Bond XTC é um revestimento aderente de poliamida termoplástico de alta temperatura.

BONDING INSTRUCTIONS

Box XTC will soften and reflow with the application of heat during or after coil winding. It is typically applied as an overcoat over a Polyurethane or Polyester type insulation basecoat to make a bondable magnet wire. Such a wire will bond to itself when heat softens the overcoat on adjacent turns and the bondcoat flows together. Upon cooling the overcoat will harden, which locks the turns in place. Bonding, if wire coated with Bond XTC should be considered reversible in that a return to high temperature will once again soften the coating.

If coils are post-baked at 180°C (356°F) for one hour, then the Bond XTC will maintain its room temperature strength until at least 140°C (284°F) and still have greater than 50% of its room temperature strength at 190°C (374°F). Post-baking of Bond XTC at lower temperatures for longer periods of time (such as 4 hours at 170°C (338°F)) is possible to optimize bond strength and coil outgassing properties. Of course, service testing should be performed to verify the adequacy of the winding constructions, the bonding process and outgassing properties.

Post-bake cycle above refers to time at temperature. Ovens of forced hot air stations may require additional time or higher temperatures to bring the wire up to the required bonding temperature.

Resistance heating of the windings by application of current is an efficient method of bonding wire. Temperatures up to 220°C (428°F) can be tolerated up to a few minutes. Again it is up to the user to optimize the bonding process.

LIMITAÇÕES DO FIO ADERENTE

Observe que o fio magnético aderente não é efetivo entre as fissuras em um enrolamento, e nem se ligará de forma adequada a menos que os condutores adjacentes estejam em contato próximo. Fio fino, 0,076–0,38 mm (0,003–0,015 pol.) e enrolamento de precisão de espirais permitem a percepção de todos os benefícios da tecnologia de fio aderente.

Disclaimer: Recommendations are for guidance only, and the suitability of a material for a specific application can be confirmed only when we know the actual service conditions. Continuous development may necessitate changes in technical data without notice. This datasheet is only valid for Sandvik materials.