

STRIP
ALLOY SURCHARGE

VALID FOR INVOICING: June

With process factor valid for finished cold rolled and hardened and tempered strip products
Since January 2016 a time lag of 45 days between market alloy prices and its alloy surcharge is used. Currency exchange rates for corresponding time period.

Sandvik	GRADE		ALLOY SURCHARGE PER KG										Lbs USD	Lbs CAD
	W.nr	ASTM	SS	SEK	EUR	GBP	USD	JPY	CAD	CNY	CHF			
Alloyed non-stainless steels and carbon steels														
15LM	1.1248	1074	1770	2,02	0,19	0,16	0,20	21,84	0,29	1,44	0,20	0,09	0,13	
20C	1.1274	1095	1870	2,06	0,19	0,17	0,21	22,29	0,29	1,47	0,20	0,09	0,13	
20C2			2258	2,33	0,22	0,19	0,23	25,16	0,33	1,66	0,23	0,11	0,15	
25C				2,05	0,19	0,17	0,21	22,20	0,29	1,47	0,20	0,09	0,13	
10C16Mo3V1				6,74	0,63	0,55	0,68	72,83	0,96	4,81	0,66	0,31	0,43	
Sanprint XP				6,07	0,56	0,49	0,61	65,64	0,86	4,34	0,60	0,28	0,39	

Martensitic stainless chromium steels														
6C27	1.4007	420	2234	5,02	0,47	0,41	0,51	54,20	0,71	3,58	0,49	0,23	0,32	
7C27Mo2				7,10	0,66	0,58	0,72	76,72	1,01	5,07	0,70	0,32	0,46	
10C28MO2				7,21	0,67	0,59	0,73	77,90	1,02	5,15	0,71	0,33	0,46	
12C27M				5,19	0,48	0,42	0,52	56,09	0,74	3,71	0,51	0,24	0,33	
12C27				4,98	0,46	0,41	0,50	53,84	0,71	3,56	0,49	0,23	0,32	
14C28N				5,08	0,47	0,41	0,51	54,91	0,72	3,63	0,50	0,23	0,33	
13C26				4,85	0,45	0,39	0,49	52,42	0,69	3,46	0,48	0,22	0,31	
19C27				4,98	0,46	0,41	0,50	53,84	0,71	3,56	0,49	0,23	0,32	

Austenitic stainless steels														
12R11	1.4310	301	2331	13,91	1,29	1,13	1,40	150,29	1,97	9,93	1,36	0,64	0,89	
11R51	1.4310	301	2231	15,24	1,42	1,24	1,54	164,65	2,16	10,88	1,49	0,70	0,98	
13RM19	EN 1.4369			14,12	1,31	1,15	1,42	152,64	2,00	10,09	1,38	0,65	0,91	
316LVM	1,4441	316LVM		27,63	2,57	2,25	2,79	298,62	3,92	19,74	2,71	1,26	1,78	
2RK65HV				41,93	3,90	3,41	4,23	453,17	5,95	29,95	4,11	1,92	2,70	
3X8R65				21,53	2,00	1,75	2,17	232,62	3,05	15,37	2,11	0,98	1,38	

Precipitation hardenable steels														
9RU10	1.4568	631	2388	14,10	1,31	1,15	1,42	152,36	2,00	10,07	1,38	0,65	0,91	
NANOFLEX				23,23	2,16	1,89	2,34	251,08	3,29	16,59	2,28	1,06	1,49	
1RK95				13,93	1,30	1,13	1,41	150,54	1,97	9,95	1,36	0,64	0,90	

Duplex stainless steels (austenitic-ferritic)														
SAF2205	EN 1.4462		2377	19,81	1,84	1,61	2,00	214,08	2,81	14,15	1,94	0,91	1,27	
SAF2507	EN 1.4410		2328	23,26	2,16	1,89	2,35	251,35	3,30	16,61	2,28	1,06	1,50	
SAF3207HD				23,82	2,22	1,94	2,40	257,42	3,38	17,01	2,33	1,09	1,53	

Ferritic stainless chromium steel														
1C429				7,18	0,67	0,58	0,72	77,54	1,02	5,13	0,70	0,33	0,46	
1C44Mo20				8,96	0,83	0,73	0,90	96,86	1,27	6,40	0,88	0,41	0,58	
0XC34				5,75	0,53	0,47	0,58	62,14	0,82	4,11	0,56	0,26	0,37	
1C34				5,71	0,53	0,46	0,58	61,66	0,81	4,08	0,56	0,26	0,37	

Nickel-base alloy														
SANICRO75X2	UNS N07750			85,99	8,00	7,00	8,67	929,25	12,19	61,42	8,42	3,93	5,53	
SAN62TiNb				74,81	6,96	6,09	7,55	808,49	10,61	53,44	7,33	3,42	4,81	
