

# EXERA® 5R10/2R25 MEDICAL WIRE WIRE

ЛИСТ ТЕХНИЧЕСКИХ ДАННЫХ

Exera® 5R10 and Exera® 2R25 are austenitic chromium-nickel stainless steels. Exera® 2R25 is a low carbon version of Exera® 5R10. The grades are characterized by:

- Good corrosion resistance
- Excellent toughness
- Good welding characteristics

## STANDARDS

- ASTM: 304, 304L
- UNS: S30400, S30403
- EN Number: 1.4301, 1.4306
- EN Name: X5CrNi18-10, X2CrNi19-11
- W.Nr.: 1.4301, 1.4306
- DIN: X5 CrNi 18 10, X2 CrNi 19 11
- SS: 2332, 2352
- AFNOR: Z6 CN 18 09, Z3 CN 18 10
- BS: 304S31

## Product standards

- ASTM F899
- ISO 16061

## APPLICATIONS

These grades are mainly used for surgical instruments and dental tools.

## CHEMICAL COMPOSITION (NOMINAL) %

	C	Si	Mn	Cr	Ni
Exera® 5R10	≤0.07	≤0.75	≤2.0	18.5	9
Exera® 2R25	≤0.03	≤0.7	≤1.5	18.5	10

## FORMS OF SUPPLY

### Wire form

- In coils with weights up to 150 kg
- On various types of spool with wire weights up to 500 kg
- In straightened lengths up to 4 m

## Surface finishes and size range

Surface finish	Size range, mm
Coated	0.20 - 8.00
Bright	0.11 - 0.80
Mechanically polished	0.40 - 6.00

## MECHANICAL PROPERTIES

Typical mechanical properties for Exera® 5R10 and Exera® 2R25 at 20°C.

Grade	Tensile strength Rm	Proof strength Rp0.2	Elongation	Hardness	
	MPa	MPa	%	HRB	HB
Exera® 5R10	≥515	≥205	≥40	≤92	≤201
Exera® 2R25	≥485	≥170	≥40	≤92	≤201

## PHYSICAL PROPERTIES

Typical physical properties for annealed Exera® 5R10 and Exera® 2R25 are given below :

Grade	Density	Elastic Modulus	Mean Coefficient of Thermal Expansion	Thermal Conductivity	Specific Heat	Resistivity
	g/cm <sup>3</sup>	10 <sup>3</sup> MPa	mm/m/°C	W/m °C	J/kg °C	μΩm
			0-100 °C	at 100 °C	0-100 °C	20 °C
Exera® 5R10/2R25	8	193	17	16	500	0.72

## CORROSION RESISTANCE

Excellent corrosion resistance in a wide range of atmospheric environments and various corrosive media.

Subject to pitting and crevice corrosion in warm chloride media and to stress corrosion cracking at temperatures above 60°C.

Considered resistant to potable water with up to approximately 200mg/l chlorides, at ambient temperatures, reducing to approximately 150 mg/l, at 60°C.

Disclaimer: Sandvik is not providing any products or services that are intended or may be construed to be recommending or otherwise advising on, in any manner, the design, suitability, appropriateness or effectiveness, from a medical/biological/safety perspective, of any medical material, instrument and/or medical device.