



SANDVIK 19.9.NbSi

WELDING WIRE

DATASHEET

Sandvik 19.9.NbSi is a filler metal mainly suited for MIG welding of stainless steels of the 18Cr/8Ni/Nb and 18Cr/8Ni/Ti types.

STANDARDS

- ISO 14343: 19 9 Nb Si
- AWS A5.9/ASME SFA-5.9: ER347Si
- W.Nr.: 1.4551

Product Approvals

- CE
- DB
- TÜV

Please note that the Werkstoff Nr. corresponds to the base material of the grade.

CHEMICAL COMPOSITION (NOMINAL) %

Chemical composition (nominal) %

C	Si	Mn	P	S	Cr	Ni	Mo	Co	Cu	N
0.04	1.0	1.3	<0.025	<0.015	19.5	10	<0.3	<0.2	<0.2	<0.050

Nb>12xC<0.75

PRODUCT APPROVALS

- CE
- DB
- TÜV

Certificates of approval, including Declaration of Performance, can be found in the Materials Center, Welding materials - approvals.

APPLICATIONS

Sandvik 19.9.NbSi is particularly suited for MIG welding. It can also be used for TIG and plasma arc welding. It is suitable for joining stainless steels of the 18Cr/8Ni/Nb and 18Cr/8Ni/Ti types. Due to the strengthening effect of niobium, this grade is recommended if the weld metal is exposed to temperatures above 400°C (750°F).

FORMS OF SUPPLY

Sandvik 19.9.NbSi is supplied as wire and straight rods

WELD METAL CHARACTERISTICS

Sandvik 19.9.NbSi gives an austenitic microstructure with approximately 8-9FN according to the WRC-92 diagram.

MECHANICAL PROPERTIES

MIG TIG – typical for non heat treated weld metal

Temperature	°C (°F)	20 (68)	400 (752)	-196 (-321)
Yield strength, R _{P0.2}	MPa (ksi)	400 (58)	320 (46)	-
Tensile strength, R _M	MPa (ksi)	610 (88)	470 (68)	-
Elongation, A ₅	%	35	23	-
Reduction in area, Z	%	61	50	-
Impact strength, Charpy V	J (ft lbs)	110 (81)	-	60 (44)
Hardness, Vickers	HV	225	-	-

CORROSION RESISTANCE

Sandvik 19.9.NbSi has good resistance to general corrosion and due to its niobium content, good resistance to intercrystalline corrosion.

FABRICATION

Recommended welding data

MIG welding

Electrode positive is used to give good penetration in all types of welded joint. The following table shows common conditions for MIG welding.

Wire diameter, mm	Wire feed, m/min	Current, A	Voltage, V	Gas, l/min
Short-arc welding				
1.0	4-8	60-140	15-21	12
Spray-arc welding				
1.0	6-12	140-220	23-28	18

We require your consent

We use cookies to personalise content and ads, to provide social media features and to analyse our traffic. We also share information about your use of our site with our social media, advertising and analytics partners. Please set your preferences in Cookie Settings and visit our Cookie Policy for more information on how and why cookies are used on this site.

[Cookie Settings](#)

Accept Cookies